

Swissmetal Boillat				
zákl.přehled slitin				
Firemní ozn.SMB	DIN ozn.dle složení	Wr.Nr.	EN ozn.dle složení	EN Wr.Nr
Nízkolegovaná měď				
C 42	CuTeP	2.1546	CuTe(P)	CW118C
C 99	CuPb1P	2.1160	-	CW113C
C 97	-	-	-	-
C 98	-	-	-	-
Mosaz s obsahem olova				
90 A	-	-	-	-
62 C	CuZn37Pb0,5	2.0337	CuZn36Pb0,5	CW604N
62 B	CuZn36Pb1,5	2.0331	CuZn36Pb1	CW600N
62 A	CuZn36Pb1,5	2.0331	CuZn35Pb2	CW601N
61 C	-	-	CuZn37Pb1,5	CW606N
61 B	-	-	CuZn35Pb2	CW606N
61 T	CuZn36Pb3	2.0375	CuZn36Pb3	CW603N
61 D	CuZn36Pb3	2.0375	CuZn36Pb3	CW603N
61 A	CuZn36Pb3	2.0375	CuZn36Pb3	CW603N
60 M	CuZn38Pb1,5	2.0371	CuZn38Pb1,5	CW608N
60 A	CuZn38Pb1,5	2.0371	CuZn38Pb2	CW608N
59 A	CuZn39Pb3	2.0401	-	-
58 H	CuZn40Pb2	2.0402	CuZn39Pb2	CW617N
58 F	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
58 A	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
58 T	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
57 B	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
59 B	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
60 T	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
mosaz vhodná pro pýchování				
E63	CuZn37	2.0321	CuZn37	CW508L
Niklová mosaz (alpaka)				
N 29	CuNi18Zn19Pb1	2.0790	CuNi18Zn19Pb1	CW408J
N 15	-	-	-	-
N 12	CuNi12Zn30Pb1	2.0780	CuNi12Zn30Pb1	CW406J
NM 6	-	-	cUn	CW407J
NM 3	CuNi7Zn39Mn5Pb3	2.0771	-	CW400J
NM 2	CuNi7Zn39Mn5Pb3	2.0771	-	CW400J
N 09	-	-	CuNi10Zn42Pb1	CW402J
M 18	CuNi18Zn20	2.0740	CuNi18Zn20	CW409J
Bronzi				
BP5	-	-	CuSn5Pb1	CW458K
BZ4	-	-	CuSn4Pb4Zn4	CW456K
BZ5	-	-	CuSn5	CW451K
Nové slitiny				
CS3	-	-	-	-
PS2	-	-	-	-
CN8	-	-	-	-
B05	-	-	-	-