

Převodní tabulka norem tvářené mědi a Cu slitin

ČSN	ozn. ČSN	ozn. DIN	Wr.Nr.	ozn. EN
Měď tvářená				
42 3000	Cu 99,95	OF-Cu	2.0040	Cu-OF
42 3001	Cu 99,9E	E-Cu 58 Cu 57	E- 2.0060	Cu-ETP
42 3002	Cu 99,95	-	-	-
42 3003	Cu 99,85 (CuP)	SF-Cu	2.0090	Cu-DHP
42 3004	Cu 99,75	-	-	-
42 3005	Cu 99,5	-	-	-
42 3209	Cu 99,2 As	-	-	-
Slitiny mědi tvářené				
42 3010	E CuSn	-	-	-
42 3013	CuSn4	-	-	-
42 3016	CuSn6	CuSn6	-	CuSn6
42 3018	CuSn8	CuSn8	-	CuSn8
42 3019	CuCd 0,2	-	-	-
42 3042	CuAl5	CuAl5As	-	CuAl5As
42 3044	CuAl9Mn2	CuAl9Mn2	-	-
42 3045	CuAl9Fe3	CuAl8Fe3	-	CuAl8Fe3
42 3046	CuAl10Fe3Mn1,5	CuAl10Fe3Mn2	-	CuAl10Fe3Mn2
42 3047	CuAl10Fe4Ni4	CuAl10Ni5Fe4	-	CuAl10Ni5Fe4
42 3048	CuAl9Ni5Fe1Mn1	-	-	-
42 3053	CuSi3Mn	-	-	CuSi3Mn
42 3054	CuNi2Si	CuNi2Si	-	CuNi2Si
42 3056	CuMn13Ni	-	-	-
42 3058	CuCd1	-	-	-
42 3063	CuNi30FeMn	CuNi30Mn1Fe	-	CuNi30Mn1Fe
42 3064	CuNi30Mn2 (nikelin)	CuNi30Mn	-	-
42 3065	CuNi45Mn2 (konstantan)	CuNi44Mn1	-	-
42 3200	CuZn4	CuZn5	-	CuZn5
42 3201	CuZn10	CuZn10	-	CuZn10
42 3202	CuZn15	CuZn15	-	CuZn15
42 3203	CuZn20	CuZn20	-	CuZn20
42 3210	CuZn30	CuZn30	-	CuZn30
42 3212	CuZn32	CuZn33	-	CuZn33
42 3213	CuZn37	CuZn37 CuZn36	-	CuZn37 CuZn36
42 3214	CuZn36Pb1	CuZn36Pb1,5	-	CuZn35Pb2
42 3220	CuZn40	CuZn40	-	CuZn40
42 3221	CuZn38Pb	CuZn38Pb0,5	-	CuZn38Pb0,5
42 3222	CuZn39Pb1	CuZn38Pb1,5	-	CuZn38Pb1 CuZn38Pb2
42 3223	CuZn39Pb2 CuZn40Pb2	CuZn40Pb2	-	CuZn39Pb2 CuZn40Pb2
42 3226	CuZn45Pb3Mn3Fe	-	-	-
42 3231	CuZn40Mn3Al1	CuZn40Al1	-	CuZn39Mn1AlPbSi
42 3234	CuZn40Mn	CuZn40Mn2	-	CuZn40Mn2Fe1
42 3237	CuZn38Sn1	CuZn38Sn1	-	CuZn38Sn1As CuZn39Sn1
42 3238	CuZn38SnMnAs	-	-	-
42 3239	CuZn28AlSnMn	-	-	CuZn40Mn2Fe1
42 3256	CuNi15Zn21	CuNi12Zn24	-	CuNi12Zn24